



Amended 10 Oct 2017

DATA SHEET - COPAL VARNISH CLEAR / VARNISH TINTED COLOURS

Description:

Africote Copal varnish clear and varnish tinted colours can be used on any wooden surface for example: Wooden doors, frames, and is especially designed to be UV stable for exterior use, both systems will highlight and protect the natural beauty of the wood and the varnish tinted colours are designed to for example a pine wooden substrate can be turned into a Mahogany wood like finish.

Surface Preparation:

Ensure surface is dry and in sound condition, free from dust, grease, oil, algae, fungus, or any loose particles.

Application:

1. Stir well and apply first coat UN thinned.
2. Stir well and apply second coat after 16 hours drying time.

Specification:

Use: Interior / Exterior

Appearance: (Satin) Finish

Drying Time: 16 hours

Recoat Time: 16 hours

Spread Rate: 10 – 12sq m/ Litre

Cleaning: Mineral Turpentine

Thinning: Not recommended

Colours:

Copal varnish: available in a clear finish

Varnish colours: Mahogany, Lt Oak, Dark oak, Teak

Packaging: 5lt Africote branded containers

Cleaning tools: Africote brush cleaner

Storage: Store in a dry, cool conditions and ensure the tin is sealed.

Caution:

1. Application must be even to avoid variation in finish.
2. Spot touch-ups will lead to variation in finish and colour.
3. Applying coats too thick can cause wrinkling and running.
4. Very cold conditions will extend drying times.

Health and Safety:

1. Keep out of reach of children.
2. Avoid swallowing. If swallowed, induce vomiting, and seek medical attention immediately.
3. Avoid eye contact. In case of eye contact, rinse eyes thoroughly with water, seek medical attention immediately.
4. Allow sufficient ventilation during application.

NB: **No** claims will be entertained where applications are done using other manufacturer's products in combination with Africote products. This includes bonding liquids, filler coats, sealers, undercoats etc.

NB: Due to ongoing research and development undertaken on our coatings and the application process, coupled with technological advances in the industry, please consult our factory to ensure you have the latest Data Sheet.

Unit 22 Sun View Centre, 7 North Reef road, Bedfordview East Germiston, P.O Box 357 Bedfordview, 2008,
South Africa

Directors: **Colin John Reeves; Roberto Paulio Ghisleni**

VIST OUR WEBSITE AT: www.africote.co.za