



Amended 21OCT 2020

DATASHEET - STOEP ENAMEL

Description:

Africote Stoep Enamel is a single pack urethane-based medium duty floor coating with a very high solid content of 55%. It consists of a urethane alkyd medium with high opacity pigments in aliphatic solvents. Tough, yet flexible, Africote Stoep Enamel resists oil and chemicals as well as foot and light traffic. Its smooth satin finish that combines easy cleaning with good slip resistance. Africote Stoep Enamel is cost-effective, easy to apply and is fast drying.

Suitable surfaces:

Typical applications include patios and garages. After appropriate preparation, Africote Stoep Enamel may be applied to old, new, and granolithic concrete, and is compatible with most previously coated substrates, but should be tested by painting a small area beforehand.

DIRECTIONS FOR USE:

SURFACE PREPARATION THOROUGH SUBSTRATE PREPARATION IS ESSENTIAL.

The surface must be clean, dry, and free from dirt, grease, and other contamination. New concrete should be left for at least 28 days before painting, and a moisture check should be carried out to ensure this lies within acceptable limits. Hard concrete or granolithic surfaces should be treated with Africote Acid Etch to improve adhesion, and any surface grease or contamination chemically removed using an Africote GP Degreaser. These treatments must be thoroughly rinsed off and the surface allowed to dry before painting. Pits and holes may be filled using cement-based filler products. Please refer to relevant Data Sheets.

MIXING:

Stir thoroughly before use.

APPLICATION:

Apply by roller or brush. If the area has not previously been treated, thin the first coat with 10% QD THINNERS to improve penetration and adhesion working well into the surface. Apply undiluted second coat. On previously sealed floors apply two full coats. On previously painted surfaces one full coat may provide adequate coverage.

AVOID APPLYING TOO THICKLY -

Two normal coats produce a far better result than one thick one, which may hinder the drying out.

DRYING TIME:

At +20°C, Africote Stoep Enamel is touch dry in approximately 3 hours, hard dry after 5 hours. Recoat after 12 hours and serviceable after 24 hours.

APPLICATION TEMPERATURE:

Do not apply below +5°C as drying time will be affected.

Africote Stoep Enamel is available in a wide range of colours.

Africote Stoep Enamel is supplied as a single pack 5L & 20L pack sizes

COVERAGE:

6-8M² per 1L

CLEANING:

Application tools may be cleaned using Africote Brush Cleaner

SHELF LIFE AND STORAGE:

Shelf Life of unopened containers is approximately 12 months subject to conditions of storage. Store in a cool, dry, frost-free environment away from sources of ignition.

DISCLAIMER:

For best colour and sheen consistency, it is highly recommended to use the same batch number. As batches may differ from final colour appearance ie: sheen, texture, colour and light reflections, application, surface texture and preparation. When doing any type of touch up work, paint corner to corner Africote will not entertain any claims otherwise.

Do not apply if there is a possibility of dew or rain within the next 4 hours. Do not apply during cold (10 degrees or wet weather)

NB: No claims will be entertained where applications are done using other manufacturer's products in combination with Africote products. This includes bonding liquids, filler coats, sealers, undercoats etc.

NB: Due to ongoing research and development undertaken on our coatings and the application process, coupled with technological advances in the industry, please consult our factory to ensure you have the latest Data Sheet.

Unit 22 Sun View Centre, 7 North Reef road, Bedfordview East Germiston, P.O Box 357 Bedfordview, 2008,
South Africa

Directors: V.P. Ghisleni, H.B. De Abreu, R.P Ghisleni
VIST OUR WEBSITE AT: www.africote.co.za